

SPECIFICATION

PROPERTIES

| Specifications | Premium Grade | | | Test Method |
|---------------------------------------|---------------|---------------|---------------|----------------|
| | LX-C3R | LX-C3Y | LX-G1R | |
| | Natural Color | Natural Color | Natural Color | |
| Mooney Viscosity ML (1+4) 100°C | 55.0-80.0 | 65.0-90.0 | 35.0-65.0 | ISO 289 - 1 |
| Specific Gravity (g/cm ³) | 0.8-1.0 | 0.8-1.0 | 1.0-1.05 | HG/T2728 |
| After Vulcanizing | | | | |
| Tensile Strength (MPa) | 10.00-14.00 | 11.00-14.50 | 11.00-14.50 | ISO 37 (Type1) |
| Modulus at 300% Elongation (MPa) | 1.00-3.00 | 1.00-3.00 | 1.00-3.00 | ISO 37 (Type1) |
| Elongation at Break (%) | 650-850 | 700-900 | 700-900 | ISO 37 (Type1) |

Remarks: 1. Sample characteristics: REFINED RUBBER (EKO RUBBER)
2. This test report shall not be reproduced in all case without the permission.

Packing : Net 20 kg./bale wrapped with HDPE Plastic

Update : 22 March 2016